

THOMSON

DELPHION

RESEARCH

PRODUCTS

INSIDE DELPHION

[Log Out](#) | [Work Files](#) | [Saved Searches](#)

[My Account](#) | [Products](#)

Search: ☐ Quick/Number ☐ Boolean ☐ Advanced

The Delphion Integrated View


Get Now: ☐ PDF | [More choices...](#)

Tools: Add to Work File:

View: [Expand Details](#) | [INPADOC](#) | Jump to:

Go to: [Derwent...](#)

- Title: **EP0417552B1: Method for stabilizing semi-finished or finished polymeric articles** [\[German\]](#) [\[French\]](#)
- Country: **EP** European Patent Office (EPO)
- Kind: **B1** Patent (See also: [EP0417552A2](#), [EP0417552A3](#))
- Inventor: None
- Assignee: **REHAU AG + Co**
[News, Profiles, Stocks and More about this company](#)
- Published / Filed: **1994-10-26 / 1990-08-30**
- Application Number: **EP1990000116601**
- IPC Code: **B29C 71/04**; [C08J 7/00](#); [B29K 23/00](#);
- ECLA Code: **B29C71/04**; [C08L9/00](#);
- Priority Number: 1989-09-14 [DE1989003930753](#)
- Abstract: [\[From equivalent EP0417552A2\]](#)
 The invention relates to a method for stabilising prefabricated semifinished products or finished articles consisting of an unsaturated polymer or of a polymer alloy which contains at least one unsaturated polymer. The semifinished products or finished articles are exposed to high-energy radiation for crosslinking and/or sterilisation. According to the invention, the unsaturated polymer is a 1,2-polybutadiene. The semifinished products or finished articles prefabricated therefrom or therewith are exposed to a maximum dose of 80 kGy.
- INPADOC [Show legal status actions](#) Get Now: [Family Legal Status Report](#)
- Legal Status:
- Designated Country: **AT BE CH DE DK ES FR GB GR IT LI LU NL SE**
- Family: [Show 8 known family members](#)
- Claims: [\[Hide claims\]](#):
 1. Application of high-energy radiation to crosslink prefabricated semi-finished products or finished articles made from an unsaturated polymer or polymer alloy containing at least one unsaturated polymer whereby the unsaturated polymer is a 1,2-polybutadiene and whereby the semi-finished products or finished articles, having a crystallinity of 15% to 29%, are exposed to a maximum radiation dose of 80 kGy for the manufacture of profiles and moulded objects for the medical and foodstuff sectors.
 2. Application as described in [claim 1](#), characterised by the fact



that irradiation takes place after the thermoforming process.

3. Application as described in [claim 1](#), characterised by the fact that the radiation dose lies between 20 and 60 kGy and is governed by the degree of crystallinity of the 1,2-polybutadiene.

[\[German\]](#) [\[French\]](#)

Other Abstract Info: CHEMABS 114(24)230263Q DERABS C1991-081843



[Nominate](#)



[this for the Gallery...](#)

© 1997-2003 Thomson Delphion

[Research Subscriptions](#) | [Privacy Policy](#) | [Terms & Conditions](#) | [Site Map](#) | [Contact Us](#)